

Rocathaan Primer OV

Description and application

Rocathaan Primer OV is a 2-component, solvent free, polyurethane primer.

As a primer for old asphalt, bituminous and cement-bound surfaces in combination with Rocathan products. Suitable for light to medium loads.

Article number and packaging

11025-5	5 kg set
11025-10	10 kg set

Properties

- Application by using a roller or brush
- Solvent-free

Properties liquid product

Colour	A component light grey B component brown transparent
Density	1,10 kg/l mixed product
Volume solids	100%
Shelf life	At least 12 months after the date of production, if stored cool in unopened packaging and protected against frost.

Application information

Method	Brush, roller
Usage	0,35 – 0,50 kg/m ² /layer <i>Surface dependent</i>
Mixing ratio	760 gram A : 240 gram B
Potlife**	Approx. 25 minutes
Application temp.	Surface +5 and +30 °C Product +10 and +25 °C
Induction time*	5 minutes
Walkable*	After 12 hours
Recoat time*	Solvent-free: min. 12 hours and max. 24 hours. Solvent-containing: min. 12 hours and max. 24 hours.
Chemical resistant*	After 7 x 24 hours
Mechanical resistant*	After 3 x 24 hours
Dilution	Not permitted
Cleaning agent	Roca Cleaner R5518 (equipment)
Hands	Swarfega Blackbox Cleaning wipes (They are also supplied by Prokol).

The times and values given are approximate and are affected by fluctuating surface and environmental conditions such as (product)temperature, relative humidity and layer thickness.

* At 20 °C and 65% RH surface.

** At 1 kg and 20 °C product.

Mixing instructions

2-component products must always be mechanically mixed, preferably with a continuously adjustable mixing machine on low speed (300 – 400 RPM) or other suitable mixing equipment. Use a clean mixing rod which matches the size of the container. Mixing too fast and too long should be avoided in order to minimise air entrapment.

First mix component A until it is a homogenous mixture. Add component B (completely drained or scraped) to component A and mix at least 2-3 minutes until it is a homogenous mixture. To exclude unmixed materials (bottom/sides) are processed, transfer the mixture to a clean mixing bucket/tub and mix again.

When using additives such as quartz sand or the like, only add when the mixture is a homogenous mixture. After adding, please mix thoroughly again.

When mixing parts, both components must be mixed separately and carefully and weighed accurately.

Notes during application

2-component products may only be applied when the relative humidity is less than 85%. The minimum surface temperature is +5° C and the temperature of the surface to be treated and the uncured product must be 3° C above the dew point. See the dew point table.

The curing process occurs more quickly at higher temperatures and slower at lower temperatures. The potlife is partly dependent on the product temperature.

Surface and circumstances

General

The surface must be clean and free of grease. All loose components must be removed.

Mineral surfaces

The surface must be absorbent in nature. The surface must be healthy, with a minimum compression strength of 25 MPa and a minimum adhesion strength of 1,5 MPa for normal used flooring.

Concrete must be at least 28 days old. Any cement skin must be removed. Closed and monolithic floors must be sanded and any dust must be removed. Remove cement skin and concrete residues by grinding or sanding.



Tel. +31 (0)85 78 200 20 • Fax. +31 (0)85 78 200 21
www.prokol.com • info@prokol.com

Liquid synthetic materials for a sustainable future

Rocathaan Primer OV

Pre-treat contaminated surfaces using flame blasting. After sanding, carefully remove dust from the surface using an industrial vacuum cleaner. Be aware that sanding can lead to filling of the pores, which can lead to reduced adhesion.

The surface must be free from pressure or rising water from the subsoil.

Moisture content surface

- cement-bound : < 4% CM (parts by weights)
- plaster-bound : < 0,5% CM (parts by weights)

Important

Projects and applications can vary greatly. Always contact your supplier if you have doubts about a certain application, choice of material or surface treatment.

All the technical information given in this technical information sheet is based on laboratory tests. Information can change, depending on the conditions.

Legal notification

The information and, in particular, the recommendations concerning the application and final use of Prokol products is issued in good faith based on Prokol's current knowledge and experience of products that are correctly stored, handled and applied under normal conditions.

In practice, the differences in materials, substrates and local conditions are such that no guarantee can be given concerning the marketability or suitability for a certain objective, nor can any liability arise from any legal relationship based on this information, nor from any written recommendations or other advice that is given. The property rights of third parties must be respected.

Prokol guarantees that its products are free from manufacturing faults. Multi-component products are a finished product once the components have been mixed and processed. When mixed and processed correctly, the product will achieve the specifications given. Prokol can only guarantee the product when surfaces are processed and pre-treated correctly.

All orders are accepted under the current sales and delivery conditions. Users must always refer to the most recent product safety information sheet and product information sheet for the product concerned.

Copies of the most recent editions are provided upon request and are available at www.prokol.com.

* At 20 °C and 65% RH surface.
** At 1 kg and 20 °C product.



Tel. +31 (0)85 78 200 20 • Fax. +31 (0)85 78 200 21
www.prokol.com • info@prokol.com

Liquid synthetic materials for a sustainable future

The publication of this product information sheet makes all previous product information sheets for this product invalid.