

Rocathaan Topcoat UP2

Description and application

2-component, solvent-containing, satin topcoating providing exceptionally durable protection, based on a special hydroxyl component and an aliphatic isocyanate hardener

A very durable protection for synthetic flooring (polyester, polyurea, polyurethane, epoxy) as well as concrete structures, such as viaducts, bridges, concrete strips, pillars, etc. in aggressive environments (industrial areas, cities etc).

Rocathaan Topcoat UP2 is also suitable as a finish on many surfaces as well as sealing littered surfaces.

Article number and packaging

16022-5	5 kg set
16022-10	10 kg set
16022-25	25 kg set (on request)

Properties

- Very high CO2 resistance against atmospheric contamination and various chemicals
- High mechanical resistance
- Smooth and tight topcoat that gives dirt little chance of adhering and makes the surface easy to clean.
- Thanks to the very low water absorption properties, it is excellent to use as a seal against penetrating moisture
- UV-resistant, therefore, gloss and colour are maintained
- Non-thermoplastic, therefore, the surface remains hard even at higher temperatures
- Easy to apply, also with a roller and brush

Properties liquid product

Colour	Available in RAL colours, see colour overview. <i>Other colours are available on project basis and on request.</i>
Finish	Satin gloss
Density	1,37 kg/l mixed product
Volume solids	Approx. 50%
Shelf life	At least 12 months after the date of production, if stored cool in unopened packaging and protected against frost.

Application information

Method	Brush, roller, air spray, airless spray
Usage	0,15 – 1 kg/m ² /layer <i>Surface dependent</i>
Mixing ratio	890 gram A : 110 gram B
Potlife**	2 hours
Visc. din cup 4	30-35 seconds
Dust-dry*	After 1 hour
Tack-free*	After 1 hour
Walkable*	After 18 hours
Recoat time*	Min. 18 hours and max. 36 hours. <i>Apply next layer within given time. Recoat times can decrease as the temperature rises.</i>
Chemical resistant*	After 7 x 24 hours
Induction time	5 minutes
Dilution	Rocathaan thinner. A maximum of 10% only to be added once base(A) and hardener(B) have been mixed. Adding thinner can affect the properties.
Cleaning agent	Roca Cleaner R5518 (equipment)

Mixing instructions

2-component products must always be mechanically mixed, preferably with a continuously adjustable mixing machine/drill (300 – 400 RPM) or another suitable mixer/whisk. As a guideline, the diameter of the mixer/whisk must be at least 1/3 of the diameter of the container in which the product is mixed in.

First mix component A until it is a homogenous mixture. Add component B (completely drained or scraped) to component A and mix at least 2-3 minutes until it is a homogenous mixture. To exclude unmixed materials (bottom/sides) are processed, transfer the mixture to a clean mixing bucket/tub and mix again.

When using additives such as quartz sand or the like, only add when the mixture is a homogenous mixture. After adding, please mix thoroughly again.

When mixing parts, both components must be mixed separately and carefully and weighed accurately.

* At 20 °C and 65% RH surface.
** At 1 kg and 20 °C product.



Tel. +31 (0)85 78 200 20 • Fax. +31 (0)85 78 200 21
www.prokol.com • info@prokol.com

Liquid synthetic materials for a sustainable future

Rocathaan Topcoat UP2

Notes during application

The ambient and surface temperature shouldn't be lower than 5 °C. Condensation on the surface reduces the adhesion. The 2-component products may only be applied when the relative humidity is less than 85%. The minimum surface temperature is +5° C and the temperature of the surface to be treated and the uncured product must be 3° C above the dew point. See the dew point table.

The curing process occurs more quickly at higher temperatures and slower at lower temperatures. The potlife is partly dependent on the product temperature.

Surface and circumstances

The surface must be clean and free of grease. All loose components must be removed. Monolithic floors must be sanded and any dust must be removed. Steel needs to be sanded and preferably blasted. Sa 2,5. dust-free blasting or diamond sanding for power-floated surfaces.

Moisture content surface

- cement-bound : < 4% CM (parts by weights)
- plaster-bound : < 0,5% CM (parts by weights)

Concrete

The concrete must be healthy, dry, grease-free and load-bearing and at least 28 days old. The concrete moisture content may be max. 4% and the temperature should be at least 5 °C. Provide the surface with a suitable primer if necessary. In certain cases, an anti-corrosion primer may be necessary.

Surfaces with dirt pickup, cement, sludge or loose sand-cement screeds (e.g. bomb ice) can be removed, for example by blasting and making the surface dust-free.

Clean contaminated and greasy surfaces (oil and grease), preferably with a steam cleaner, using a suitable cleaning agent. If this does not result in a clean, load-bearing surface, blasting and, in certain cases, milling should be performed.

Repairs and equalizations must be carried out professionally with the appropriate products, also with regard to the finishing layer. Any expansion joints in the surface may not be concealed, but must retain their function.

The load-bearing capacity of the synthetic floor depends on the compressive strength of the cement-bound screed and can never be absorbed by a flooring system.

Already existing and treated work:

Roughen old 2-component layers by blasting or sanding and apply a suitable primer. Check old coating layers for possible detachment. If in doubt, always set up a test area and consult your supplier.

Important

Projects and applications can vary greatly. Always contact your supplier if you have doubts about a certain application, choice of material or surface treatment.

All the technical information given in this technical information sheet is based on laboratory tests. Information can change, depending on the conditions.

Legal notification

The information and, in particular, the recommendations concerning the application and final use of Prokol products is issued in good faith based on Prokol's current knowledge and experience of products that are correctly stored, handled and applied under normal conditions.

In practice, the differences in materials, surfaces and local conditions are such that no guarantee can be given concerning the marketability or suitability for a certain objective, nor can any liability arise from any legal relationship based on this information, nor from any written recommendations or other advice that is given. The property rights of third parties must be respected.

Prokol guarantees that its products are free from manufacturing faults. Multi-component products are a finished product once the components have been mixed and processed. When mixed and processed correctly, the product will achieve the specifications given. Prokol can only guarantee the product when surfaces are processed and pre-treated correctly.

All orders are accepted under the current sales and delivery conditions. Users must always refer to the most recent product safety information sheet and product information sheet for the product concerned.

Copies of the most recent editions are provided upon request and are available at www.prokol.com.

The publication of this product information sheet makes all previous product information sheets for this product invalid.

* At 20 °C and 65% RH surface.
** At 1 kg and 20 °C product.



Tel. +31 (0)85 78 200 20 • Fax. +31 (0)85 78 200 21
www.prokol.com • info@prokol.com

Liquid synthetic materials for a sustainable future