

Rocathaan Hotspray PA 45-BA

Description and application

Slow set hotspray coating, based on pure, aromatic polyurea. This product takes longer to dry, which means it is possible to add mineral scatter materials to the still, wet coat.

If desired, this product can be used directly as a sealer or topcoating in order to seal littered surfaces.

Littered, adhesive layer and sealer/topcoat for mineral aggregate for indoor and outdoor applications, such as bridge decks, parking decks, car parks, driveways, RORO-systems and loading platforms.

Article number and packaging

19055-20	39,6 kg set
19055-200	447,5 kg set

Properties

- Pure polyurea
- Large reach of layerthickness
- Relatively long wet phase, for ease of gritting
- Brief curing time

50% Modulus	4,5 Mpa
100% Modulus	5,9 Mpa
200% Modulus	8,3 Mpa
Elongation	± 475% (DIN 53504)
Tensile strength	± 14,7 MPa (DIN 53504)
Shore hardness	A93 ± 5 (DIN 53505, ASTM D2240) D44 ± 5 (DIN 53505, ASTM D2240)
Wear resistance taber	64 mg (1000, 1 kg load, CS17)
MU Value	1000
Fire class	B2 (DIN 4102)

Properties liquid product

Colour	Approx. RAL 7032 <i>Other colours are available on project basis and on request.</i>
Density	1,12 kg/l mixed product
Volume solids	100%
Flash point	>80 °C
Shelf life	At least 12 months after the date of production, if stored cool in unopened packaging and protected against frost.

Application information

For processing a multi-component dosing system with heated tube set and a static mixing gun with diffuser for equal distribution, or a high-pressure gun is used.

The pressure and temperature given serve as guidelines only. You must verify these values in practice and adjust them in line with the circumstances.

Respect the open time during which mineral materials can be gritted, as it may otherwise result in bald patches in the anti-slip finish.

Reaction time	5 - 6 min. high pressure gun 5 - 6 min. static mixing gun
Tack free	10 - 15 minutes
Spraying temperature	65 - 85 °C with a high pressure gun 40 - 50 °C with a static mixing gun
Hose temperature	65 - 85 °C with a high pressure gun 40 - 50 °C with a static mixing gun
Spraying pressure	<i>Depending on the type of pistol and mixing chamber.</i> - Fusion CS gun 130 - 140 bar - Fusion AP gun 160 - 180 bar - Static mixing gun 30 - 50 bar
Usage	1,12 kg/m ² /mm <i>Usage must be adjusted to the grain size of the gritting material, whereby 2/3 of the grain must be encapsulated.</i>
Mixing ratio	1:1 in volume
Surface temperature	Minimum +5 °C
Open time*	With the same product: Almost directly and max. within 24 hours Solvent free: min. 24 and max. 36 hours Solvent-containing: min. 3 and max. 36 hours. <i>Open times can decrease as the temperature rises. When exceeding the open time, the existing layer must be sanded and provided with a suitable primer.</i>
Chemical resistant*	After 3 x 24 hours <i>Each Prokol product has varying levels of resistance to specific chemicals. Chemical concentrations are complex and are strongly influenced by the environment and temperature. Contact Prokol technical support for specific recommendations.</i>
Mechanical resistant*	After 3 x 24 hours
Cleaning agent	Roca Cleaner N6500-P (equipment)
Rinsing agent	Roca Cleaner TC-N

* At 20 °C and 65% RH surface.
** At 1 kg and 20 °C product.



Tel. +31 (0)85 78 200 20 • Fax. +31 (0)85 78 200 21
www.prokol.com • info@prokol.com

Liquid synthetic materials for a sustainable future

Rocathaan Hotspray PA 45-BA

Mixing instructions

First mix component A until it is a homogenous mixture. The mixing time depends on the size of packaging. A 200 liter drum, used for the first time or after a longer storage period, should be mixed intensively for 45 minutes. Following this, short and thorough mechanical mixing at every turn is sufficient.

Non-homogenous mixed products lead to deviating features in the end-result subsequently.

Notes during application

Do not inhale spray mist. Ensure respiratory equipment designed for the conditions is worn while spraying.

2-component products may only be applied when the relative humidity is less than 85%. Condensation on the surface reduces the adhesion. The minimum surface temperature is +5° C and the temperature of the surface to be treated and the uncured product must be 3° C above the dew point. See the dew point table.

Surface and circumstances

The surface must be clean, dry and free from grease. A screed based Rocathaan Hotspray PA 45-BA must be applied within the given open time of the previous layer taking in account that Rocathaan Hotspray PA 45-BA is solvent-free. If this proves impossible, the previous layer must be sanded mechanically and covered with a suitable primer.

The choice of primer depends on the surface. In that case, consult the primer selection table or get in contact for advice.

The surface must be healthy, with a minimum compression strength of 25 MPa and a minimum adhesion strength of 1,5 MPa. The surface must be clean and free of grease. All loose components must be removed. Concrete and anhydrite needs to be at least 28 days old.

Any cement skin must be removed. Monolithic floors must be sanded and any dust must be removed. Surfaces with dirt pickup, or loose sand-cement screeds (e.g. bomb ice) can be removed, for example by blasting and making the surface dust-free.

Clean contaminated and greasy surfaces (oil and grease), preferably with a steam cleaner, using a suitable cleaning agent. Rinse well with clean tap water. If this does not result in a clean, load-bearing surface, blasting should be performed.

The surface must be free from pressure or rising water from the subsoil.

Moisture content surface

- cement-bound : < 4% CM (parts by weights)
- plaster-bound : < 0,5% CM (parts by weights)

If a topcoating is going to be applied as a finishing layer, it must be suitable for the purpose and elasticity of the surface.

Rocathaan Hotspray PA 45-BA can be used as a simple screed on various surfaces, where it may not be seen as a waterproof finish.

There are various types of surfaces. Some of which have their own individual pre-treatment requirements. If in doubt, getting in contact with your supplier is advised.

Aromatic products are not fully colour/UV-proof and will slightly discolorise when exposed to UV light. If this is not desired, adding a aliphatic topcoating as finish layer based on the elasticity of this product is advised.

For detailed information regarding pre-treatment of the surfaces, please see the "surface pre-treatment" information sheet.

Important

Projects and applications can vary greatly. Always contact your supplier if you have doubts about a certain application, choice of material or surface treatment.

All the technical information given in this technical information sheet is based on laboratory tests. Information can change, depending on the conditions.

Legal notification

The information and, in particular, the recommendations concerning the application and final use of Prokol products is issued in good faith based on Prokol's current knowledge and experience of products that are correctly stored, handled and applied under normal conditions.

In practice, the differences in materials, surfaces and local conditions are such that no guarantee can be given concerning the marketability or suitability for a certain objective, nor can any liability arise from any legal relationship based on this information, nor from any written recommendations or other advice that is given. The property rights of third parties must be respected.

Prokol guarantees that its products are free from manufacturing faults. Multi-component products are a finished product once the components have been mixed and processed. When mixed and processed correctly, the product will achieve the specifications given.

* At 20 °C and 65% RH surface.
** At 1 kg and 20 °C product.



Tel. +31 (0)85 78 200 20 • Fax. +31 (0)85 78 200 21
www.prokol.com • info@prokol.com

Liquid synthetic materials for a sustainable future

Rocathaan Hotspray PA 45-BA

Prokol can only guarantee the product when surfaces are processed and pre-treated correctly.

All orders are accepted under the current sales and delivery conditions. Users must always refer to the most recent product safety information sheet and product information sheet for the product concerned.

Copies of the most recent editions are provided upon request and are available at www.prokol.com.

The publication of this product information sheet makes all previous product information sheets for this product invalid.

* At 20 °C and 65% RH surface.
** At 1 kg and 20 °C product.



Tel. +31 (0)85 78 200 20 • Fax. +31 (0)85 78 200 21
www.prokol.com • info@prokol.com

Liquid synthetic materials for a sustainable future