

# Rocathaan Hotspray PA 400

## Description and application

Rocathaan Hotspray PA 400 is a quick-curing, solvent-free hotspray coating/liner based on aromatic polyurea,

Can be used as protection/lining for basins, tanks, façades and many other applications including ramps and parking roofs. Also suitable as coating for a variety of insulation material, metal and different kinds of wood.

## Article number and packaging

19403-200 447,5 kg set (colourless product)  
4,5 kg Prokol Hotspray Color Pasta

## Properties

- Tack free in seconds and walkable in minutes
- Can be applied under extreme conditions
- Rapid return to service
- Insensitive to moisture and humidity
- Wear resistant
- Good chemical resistance against acids and alkalis
- Low temperature flexibility
- Completely solvent-free
- UV-resistant
- Seamless membrane
- Excellent thermal stability

50% Modulus	9 MPa
100% Modulus	11 MPa
200% Modulus	15 MPa
Elongation	± 350% (DIN 53504)
Tensile strength	± 20 MPa (DIN 53504)
Shore hardness	A96 ± 5 (DIN 53505, ASTM D2240)
Wear resistance taber	15 mg (1000, 1 kg load, CS17) (EN ISO 5470-1)
MU Value	1000
Fire class	B2 (DIN 4102)

## Properties liquid product

Colour	Available in RAL colours, see colour overview. <i>Other colours are available on project basis and on request.</i>
Density	1,12 kg/l mixed product
Volume solids	100%
Flash point	>80 °C
Shelf life	At least 12 months after the date of production, if stored cool in unopened packaging and protected against frost.

## Application information

Is processed with multi-component (hotspray) high pressure equipment using a suitable spray gun. This equipment must be adjusted for the product to be sprayed and capable of supplying sufficient pressure. The spray temperature and layer thickness strongly influence the reaction time, curing and treatment.

Reaction time	Approx. 5 seconds
Tack free	30 - 45 seconds
Spraying temperature	70 - 85 °C
Hose temperature	70 - 85 °C
Spraying pressure	<i>Depending on the type of pistol and mixing chamber.</i> <ul style="list-style-type: none"><li>- Fusion CS gun 130 - 140 bar</li><li>- Fusion AP gun 150 - 180 bar</li></ul>
Usage	1,12 kg/m <sup>2</sup> /mm <i>Depending on the circumstances, surface and desired results.</i>
Mixing ratio	1:1 in volume
Surface temperature	Min. +5 °C
Open time*	With the same product: Almost directly and max. within 24 hours Solvent free: min. 24 and max. 36 hours Solvent-containing: min. 3 and max. 36 hours. <i>Open times can decrease as the temperature rises. When exceeding the open time, the existing layer must be sanded and provided with a suitable primer.</i>
Chemical resistant*	After 7 x 24 hours <i>Each Prokol product has varying levels of resistance to specific chemicals. Chemical concentrations are complex and are strongly influenced by the environment and temperature. Contact Prokol technical support for specific recommendations.</i>
Mechanical resistant*	After 2 x 24 hours
Cleaning agent	Roca Cleaner N6500-P (equipment)
Rinsing agent	Roca Cleaner TC-N

\* At 20 °C and 65% RH surface.  
\*\* At 1 kg and 20 °C product.



Tel. +31 (0)85 78 200 20 • Fax. +31 (0)85 78 200 21  
www.prokol.com • info@prokol.com

**Liquid synthetic materials for a sustainable future**

# Rocathaan Hotspray PA 400

## Mixing instructions

The temperature of the materials in the drums need to be at least 15 °C with a maximum of 35 °C.

If the materials are too cold, use the heaters of the spraying equipment to heat them up.

**Be aware!** Start by mixing the A (base) component intensively for 20 minutes before starting heating and circulating the materials through the pump. Use a Twistork-helix mixer to obtain a homogeneous mixture.

The mixing time depends on the size of packaging. A 200 liter drum, used for the first time or after a longer storage period, should be mixed intensively for 45 minutes. Following this, short and thorough mechanical mixing at every turn is sufficient.

Non-homogenous mixed products lead to deviating features in the end-result subsequently.

## Notes during application

Do not inhale spray mist. Ensure respiratory equipment designed for the conditions is worn while spraying.

2-component products may only be applied when the relative humidity is less than 85%. Condensation on the surface reduces the adhesion. The minimum environment and surface temperature is +5° C and the temperature of the surface to be treated and the uncured product must be 3° C above the dew point. See the dew point table.

## Surface and circumstances

Moisture content surface

- cement-bound : < 4% CM (parts by weights)
- plaster-bound : < 0,5% CM (parts by weights)

For detailed information regarding pre-treatment of the surfaces, please see the "surface pre-treatment" information sheet.

## Important

Projects and applications can vary greatly. Always contact your supplier if you have doubts about a certain application, choice of material or surface treatment.

\* At 20 °C and 65% RH surface.  
\*\* At 1 kg and 20 °C product.



All the technical information given in this technical information sheet is based on laboratory tests. Information can change, depending on the conditions.

## Legal notification

The information and, in particular, the recommendations concerning the application and final use of Prokol products is issued in good faith based on Prokol's current knowledge and experience of products that are correctly stored, handled and applied under normal conditions.

In practice, the differences in materials, surfaces and local conditions are such that no guarantee can be given concerning the marketability or suitability for a certain objective, nor can any liability arise from any legal relationship based on this information, nor from any written recommendations or other advice that is given. The property rights of third parties must be respected.

Prokol guarantees that its products are free from manufacturing faults. Multi-component products are a finished product once the components have been mixed and processed. When mixed and processed correctly, the product will achieve the specifications given. Prokol can only guarantee the product when surfaces are processed and pre-treated correctly.

All orders are accepted under the current sales and delivery conditions. Users must always refer to the most recent product safety information sheet and product information sheet for the product concerned.

Copies of the most recent editions are provided upon request and are available at [www.prokol.com](http://www.prokol.com).

The publication of this product information sheet makes all previous product information sheets for this product invalid.



Tel. +31 (0)85 78 200 20 • Fax. +31 (0)85 78 200 21  
[www.prokol.com](http://www.prokol.com) • [info@prokol.com](mailto:info@prokol.com)

**Liquid synthetic materials for a sustainable future**